



## Material Spreading Rates Per Square Metre

Total Surface	Black Base Layer			Coloured Top Layer		
	Depth mm	SBR 2:6mm kg	Binder 10% kg	Depth mm	EPDM 1:4mm kg	Binder 20% kg
35 mm depth	20	12.50	1.25	15	12.50	2.50
45 mm depth	30	18.75	1.88	15	12.50	2.50
55 mm depth	40	25.00	2.50	15	12.50	2.50
65 mm depth	50	31.25	3.13	15	12.50	2.50
70 mm depth	55	34.38	3.44	15	12.50	2.50
75 mm depth	60	37.50	3.75	15	12.50	2.50
90 mm depth	75	46.88	4.69	15	12.50	2.50
100 mm depth	85	53.13	5.31	15	12.50	2.50

A less open surface finish for pool surrounds can be achieved using a granule size of 0.5:1.5 mm:

Coloured Top Layer		
Depth mm	EPDM 0.5:1.5 kg	Binder 22% kg
5	5.50	1.41

- 1 Spreading rates are dependant on the sub base and installer techniques, **Monkey Proof®** does not warrant spreading rates.
- 2 The binder ratio for black EPDM installations must be increased by volume to allow for the lower specific gravity.